N-TYPE TOPCon Technology



565-590WP HIGH PERFORMANCE GLASS-GLASS SERIES **BIFACIAL SERIES**

MBB HALF-CUT BIFACIAL TOPCon CELL MONOCRYSTALLINE MODULE



UP TO 22.8% MODULE EFFICIENCY



BIFACIAL TOPCON CELL GAIN





HIGH OUTPUT POWER



LOW LID

SUNART PV

Lampart Lighting is which maintains its position as a leader in the lighting sector with the projects it has completed all over the world, was put into operation in 2023 with the aim of being the leading company in the Solar Panel Production Sector with our 30 years of experience and our state-of-the-art production line. Sunart Energy is a high-efficiency panel manufacturer whose mission is to develop photovoltaic R&D studies and renewable and sustainable energy. With our state-of-the-art production line, our modules have the highest quality standards.



HALF - CUT TOPCon TECHNOLOGY

Half - cell TOPCon technology modules reduce power loss, while 3 - piece junction box provides better performance in shadowing conditions.



REDUCED HOT SPOT LOSS

Optimized electrical design and lower operating current for reduced hot spot loss and better temperature coefficient.



ENHANCED MECHINAL LOAD

Excelent wind load 2400Pa & snow load 5400Pa under certain installation method



MULTI BUSBAR TECHNOLOGY

Less power loss by minimizing the shading impact







QUALIFICATIONS & CERTIFICATES

IEC 61215. IEC 61730-1/-2. IEC 61701. IEC 62716. IEC 62804 PID ISO 45001:2018, ISO 9001:2015, ISO 14001:2015













MECHANICAL DATA

Cell Type	N Type TOPCon
Cell Size	182x91mm
Number of Cells	144 (6x24), Half Cut
Dimensions (LxWxH)	2279x1134x30mm (89.7x44.6x1.18 inches)
Weight	32.5kg <u>+</u> 1kg
Glasses	3.2/2.2mm,AR coating, Low iron, Tempered
Frame	Anodized Aluminium
Junction Box	IP68, 1500VDC, 3 Schottky bypass diodes
Cable Diameter (IEC/UL)	4mm2 / 12AWG
Cable Lenght	Customized; (-)350/(+)350mm
Connector Type	MC4 / MC4 Compatible

OPERATING PARAMETERS Operating Temperature Range 40°C to 105°C

operating remperature number	-40 G (U +00 G
Maximum System Voltage	1500VDC (IEC)
Maximum Series Fuse Rating	30A
Power Output Tolerances (Pmax)	0/+5W
Maximum Power Bifaciality	70±5%





ELECTRICAL DATA WITH BIFACIAL GAIN

Module type	ART144-MB-GB-M	ART144-MB-GB-M	ART144-MB-GB-M	ART144-MB-GB-M	ART144-MB-GB-M	ART144-MB-GB-M
Maximum power (Pmpp/wp) *	565	570	575	580	585	590
Bifacial Gain 5% / 15% / 25% **	593 / 621 / 649	598 / 627 / 655	603 / 632 / 660	609 / 638 / 667	614 / 643 / 672	619 / 649 / 678
Open circuit voltage (Voc) * Bifacial Gain 5% / 15% / 25% **	50.70	50.85	51.05	51.25	51.40	51.60
	50.90	51.00	51.30	51.50	51.60	51.80
Short circuit current (Isc) *	13.90	13.95	14.03	14.09	14.12	14.21
Bifacial Gain 5% / 15% / 25% **	14.3 / 15.0 / 15.6	14.4 / 15.1 / 15.8	14.5 / 15.2 / 15.9	14.6 / 15.3 / 16.0	14.8 / 15.4 / 16.2	14.9 / 15.5 / 16.3
Maximum power voltage (Vmpp) * Bifacial Gain 5% / 15% / 25% **	42.65	42.76	42.95	43.13	43.31	43.47
	43.4 / 43.6 / 43.7	43.5 / 43.7 / 43.8	43.6 / 43.7 / 43.9	43.7 / 43.9 / 44.1	44.1 / 44.2 / 44.3	44.2 / 44.3 / 44.4
Maximum power current (Impp) *	13.25	13.33	13.39	13.45	13.51	13.59
Bifacial Gain 5% / 15% / 25% **	13.66 / 14.24 / 14.85	13.74 / 14.34 / 14.95	13.83 / 14.46 / 15.03	13.93 / 14.53 / 15.12	13.92 / 14.54 / 15.16	14.00 / 14.65 / 15.27
Module efficiency (%) * Bifacial Gain 5% / 15% / 25% **	21.8%	22.0%	22.2%	22.4%	22.6%	22.8%
	22.9 / 24.0 / 25.1	23.1 / 24.2 / 25.3	23.3 / 24.4 / 25.5	23.5 / 24.6 / 25.8	23.7 / 24.8 / 26.0	23.9 / 25.1 / 26.2

^{*} STC Conditions: Irradiance 1000W/m2, Cell temperature 25C, Air Mass AM1.5 according to EN 60904-3


THERMAL CHARACTERISTICS

Temperature Coefficient (Pmpp)	-0.35%/°C
Temperature Coefficient (Voc)	-0.28%/°C
Temperature Coefficient (Isc)	+0.048%/°C

PACKAGING CONFIGURATION

	40 ft (HQ)	20 ft	
Number of modules per container	792	180	
Number of modules per pallet	36	36	
Number of pallets per container	22	5	
Box dimensions (LxWxH)	2320x1150x1290	2320x1150x1290	
Box gross weight (kg)	1200	1200	

LINEAR PERFORMANCE WARRANTY




Mounting Holes 30

30


silicon filling

module

I-V CHARACTERISTICS AT DIFFERENT IRRADIATIONS



I-V CHARACTERISTICS AT DIFFERENT TEMPERATURES



© 2023 Sunart PV Modul Tech. All rights reserved. Spacifications included in this datasheet are subject to change without notice. Please contact our company to use the latest version for contact.





^{**} Bifacial Gain: The additional gain from the back side compared to the power of the front side at standart test condition. It depends on mounting (structure, height, tilt angle etc.) and albedo of the ground.